

Cont .. 2 ..

- Coverage :: 6.5M² / Litre / Coat.
- Drying Time – Touch :: 15 – 30 Mins.
- Hard :: 4 - 6 Hours
- Pot Life :: Approximately 40 minutes at 30°C.
- Curing Time :: 7 Days
- Packing :: 20 litres
- Storage Life :: Up to 6 (Six) months, as long as the sealed containers are kept under cover in a dry place under normal temperature conditions.

APPLICATION DATA

Surface Preparation

Concrete / steel surface should be cleaned by any suitable method (like sand blasting, water jetting etc) to remove old coatings, grease, oil, curing compounds, loose particles, weld spatter, flux, rust etc.

APPLICATION

Stir base thoroughly and then mix three parts base and one part catalyst by volume to uniform consistency. Allow the mixture to mature for 30 minutes and still again before application and occasionally during use.

- Brush/Roller :: Apply without thinning
- Conventional Spray :: Normally no thinning is required. Use any standard equipment at an atomizing pressure of 3.5 – 4.2 kg/ cm².
- Airless Spray :: Apply without thinning. Use any standard equipment having pump Ratio : 30:1. Tip Size: 0.38 – 0.43mm. Tip Pressure 100 – 160 kg/cm².
- Safety & precaution :: Please refer to the separate safety data sheet available with detailed information.

TECHNICAL SERVICE :

SWC group maintains a technical division with highly qualified technical personnel to investigate and advise on subjects related to Concrete and the Construction Industry. The Division can advise on the correct use and selection of right products at the right place.

SWC undertakes Consultancy Service for diagnosis and rehabilitation of distressed structures. SWC undertakes Contracts on turnkey basis for total Waterproofing System with guarantee

NOTE : This Technical data sheet is to be used as guidance only. Although the basic formulation of the product remains unchanged, production refinements arising from continuing research and evaluation programmes may occasionally result in marginal change in properties. The recommendation and properties of the product based on continuous monitoring of the product are not intended to infringe on other patents.

THE STRUCTURAL WATERPROOFING CO.PVT.LTD.

- Regd. Office : 21/1 Dover Road Calcutta- 700 019 **Dial :** 2475-2684/5378/9950, **Fax :** 2475- 8240
- Calcutta : Plot 38/1, Block-GN, Sector IV & V, Salt Lake City, Calcutta- 700 091
Dial : 2357- 3546/3547 , **Fax:** 2357 3881
- Delhi Office : 406, Deepali, 92, Nehru Place, New Delhi - 110 019, **Dial:** 26445680 & 26435432 **Fax:** 26416861
- Mumbai Office : 56, Mahavir Centre, Sector -17, Vashi , Navi Mumbai - 400 703,
Dial: 27893601 **Fax:** 27893571 **E-mail:** swcbom@bom5.vsnl.net.in
- Chennai Office : 81, 3rd Floor, A, Sulochana Terrace, 1st Main Road, Gandhi Nagar, Adayar,
Chennai-600 020 **Dial.** 24423731 **Fax:** 24422476
- Bangalore Office : 104, Victoria View, Borewel Road, White Field, Bangalore – 560 066.
Telefax : 080 – 3310112, **Email :** swcbangalore@yahoo.co.in